Crack-resistant laminated board prodn. for PCB - by immersing substrate in flexible thermoplastic resin compsn. contg. inorganic filler, piling substrates and laminating

Patent Assignee: MATSUSHITA ELECTRIC WORKS LTD (MATW ) Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No Kind Date Applicat No Kind Date Week
JP 5286093 A 19931102 JP 9294645 A 19920415 199348 B

Priority Applications (No Type Date): JP 9294645 A 19920415 Patent Details:

Patent No Kind Lan Pg Main IPC Filing Notes JP 5286093 A 5 B32B-027/20

Abstract (Basic): JP 5286093 A

Laminated board is produced by immersing a substrate in a flexible thermoplastic resin compsn. comprising 100 pts. wt. resin and 5-50 pts. wt. of inorganic filler having an av. particle dia. of up to 1 microns and the maximum particle size of up to 2.5 um, by piling a plurality of the substrate and by laminating them.

USE/ADVANTAGE - The laminate board can be bent inside or out side without crack generation. The board can be pref. used for producing printed circuit board. In an example, a flexible unsatd. polyester resin was added by 20 wt.% of Sb203 having an av. particle dia. of 0.9 microns and max. dia. of 1.8 microns. A mixed nonwoven fabric made of glass fibres and polyester fibres and a glass fibre/cloth separately was impregnated by the resin. Two impregnated mixed fabrics were put on both side of impregnated glass fiber cloth and a copper foil was arranged on both out sides of the fabrics and pressed between pair of laminate rolls and heated at 100 deg.C for 20 min. and 160 deg.C for 20 min. to cure in an oven. The laminated board obtd. showed minimal radius of 8 m inside and 7 mm outside on 180 deg. bending without wrinkle generation.

Dwg.0/0

Title Terms: CRACK; RESISTANCE; LAMINATE; BOARD; PRODUCE; PCB; IMMERSE; SUBSTRATE; FLEXIBLE; THERMOPLASTIC; RESIN; COMPOSITION; CONTAIN; INORGANIC; FILL; PILE; SUBSTRATE; LAMINATE

Derwent Class: A23; A85; L03; P73; V04

International Patent Class (Main): B32B-027/20

International Patent Class (Additional): B29B-011/16; B29B-015/08;
B29K-105-06; B32B-005/28; B32B-007/02; C08J-005/10; H05K-001/03

File Segment: CPI; EPI; EngPI